



CÔNG TY TNHH XNK TỔNG HỢP VI KHANH

VI KHANH IMPORT - EXPORT Co., Ltd

Head Office: 281/39/4 Le Van Sy Street, Tan Binh District, HCMC, Vietnam

Tel: (08) 39914713 - 39912025

Fax: (08) 39914791

Email: info@vikhanh.com.vn

Website: www.vikhanh.com.vn

www.vikhanh.com.vn

Type of cement		Asia	Asia	Asia
Cement (kg)		400	340	340
Sand (kg)		575	585	650
Stone (kg)		1070	1090	1130
Water/Cement Ratio		0.59	0.69	0.6
Admixture 1 & dosage		BLANK	BLANK	BC-100
				0.38% by wt.
Loss in slump (mm)	5min	190	195	215
	1hr	95	155	160
Air content (%)	5min	0.9	0.9	2.5
Setting time (hr)	Initial	7.03	7.18	6.35
	Final	8.23	8.37	8.05
Compressive	4days	30	21	32.2
Strength, MPa	7days	34.6	25.4	41.3
	28 days	43.3	34.7	46.7

www.vikhanh.com.vn

www.vikhanh.com.vn

www.vikhanh.com.vn